

# PRE-ELEC<sup>®</sup> ABS 1410

ABS injection moulding compound  
Electrically conductive

Applications: Technical parts

PRE-ELEC<sup>®</sup> ABS 1410 is a conductive thermoplastic compound based on ABS. Conductivity is achieved by using special conductive carbon black. In addition to a low electrical resistivity it has excellent mechanical properties and is easy to injection mold.

Special properties	Unit	Value	Method
Volume resistivity	Ω.cm	350	PRE021
Surface resistance	Ω	5E+03	IEC 61340-2-3

General properties	Unit	Value	Method
Specific gravity	g/cm <sup>3</sup>	1.10	ISO 1183
Melt flow rate at 220°C	g/10 min		ISO 1133
10.0 kg		15.0	
Mould shrinkage	%	0.5 - 0.8	ISO 294-4
Vicat, Rate A	°C	104	ISO 306/A50
Vicat, Rate B	°C	91	ISO 306/B50
HDT, 0.45 MPa	°C	88	ISO 75/Bf
HDT, 1.80 MPa	°C	73	ISO 75/Af

Mechanical properties	Unit	Value	Method
Tensile strength (*)	MPa	36	ISO 527
Tensile strain at break (*)	%	8	ISO 527
Flexural modulus	MPa	2000	ISO 178
Impact strength, Charpy	kJ/m <sup>2</sup>		ISO 179
Unnotched, +23°C		33	
Notched, +23°C		5	
Unnotched, -20°C		21	
Notched, -20°C		2	
Hardness, Shore D	-	76	ISO 868

MFR is measured from granulates

Test specimen: injection moulded rod; Thickness: 10 mm, width: 4 mm

\*) extruded tape; Thickness 600-800 µm

# PRE-ELEC<sup>®</sup> ABS 1410

This product is REACH and RoHS compliant

Visit Premix Data Center for more detailed information of our products at [www.premixgroup.com/data-center-main](http://www.premixgroup.com/data-center-main)

## Processing instructions

	Unit	Processing range	
Injection moulding			
Material temperature	°C	220	- 260
Mould temperature	°C	60	- 90
Injection pressure	Bar	750	- 1200
Injection speed			moderate

## Notes

Drying of the product is recommended for 2-4 hours at 80-100°C prior to use.

Processing conditions as with filled ABS. These parameters are for guidance only. The process parameters should always be optimized for the used equipment. The instructions of the equipment manufacturer should be followed. Caution should be taken when handling molten material as it is extremely hot and may cause severe burns. Overheated material can be cooled with e.g. water.

## Storage

Product-specific details are mentioned in the notes above. The general minimum shelf life for Premix's product is 3 years with the following conditions: 1) original package is unopened, 2) the storage area and conditions provide protection from direct sunlight and significant changes in storage temperature, 3) the product is pre-dried accordingly before use.

The information in this datasheet represents typical values obtained by us, and shall not be regarded as a product specification. The right to make any changes to the content and appearance of this document is reserved by Premix Oy. We condition that the product will be inspected and qualified by the customer for their process to meet the specific requirements set by application, processing equipment and the end product. The user of this product is held responsible for the evaluation of this product's suitability concerning applied legislation and possible patent infringements. We do not intentionally add or incorporate hazardous substances in our production.

PRE-ELEC<sup>®</sup> is a registered trademark of Premix.