

Item Description

Item ID

PRE-ELEC[®] TP 14815
TP14815

PP extrusion compound
Electrically conductive
Flame retardant

Typical end product
Applications

Pipes, Sheets
Ventilation systems
ATEX

PRE-ELEC[®] TP 14815 is a carbon black filled electrically conductive polypropylene compound with flammability rating of V-0 at 3 mm specimen thickness according to UL94 categories. The flame retardancy has been achieved with non-halogenated flame retardant agents.

Special properties	Unit	Value	Method
Volume resistivity	Ω.cm	110	PRE021
Surface resistance(*)	Ω	2E+03	IEC 61340-2-3
Flammability	-	V-0 (3 mm)	RD524

General properties	Unit	Value	Method
Specific gravity	g/cm3	1,42	ISO 1183
Melt flow rate at 230°C 10.0 kg	g/10 min	1,3	ISO 1133
Mould shrinkage	%	0.9 - 1.1	ISO 294-4
Vicat, Rate A	°C	133	ISO 306/A50
Vicat, Rate B	°C	64	ISO 306/B50
HDT, 0.45 MPa	°C	72	ISO 75/Bf
HDT, 1.80 MPa	°C	48	ISO 75/Af

Mechanical properties	Unit	Value	Method
Tensile strength(*)	MPa	15	ISO 527
Tensile strain at break(*)	%	300	ISO 527
Flexural modulus	MPa	2000	ISO 178
Impact strength, Charpy Unnotched, +23°C	kJ/m2	NB	ISO 179
Notched, +23°C		7	
Hardness, Shore A	-	> 90	ISO 868
Hardness, Shore D	-	67	ISO 868

MFR is measured from granulates

Test specimen: injection moulded rod; Thickness: 10 mm, width: 4 mm

*) extruded tape; Thickness 600-800 µm

Item Description

Item ID

PRE-ELEC[®] TP 14815
TP14815

Visit Premix Data Center for more detailed information of our products at www.premixgroup.com/data-center-main

Processing instructions

	Unit	Processing range
Extrusion		
Cylinder temperature profile	°C	220 - 255
Die temperature profile	°C	240 - 255
Tool/Roll temperature	°C	90 - 60

Notes

Drying of the product is recommended for 2-3 hours at 90°C prior to use.

These parameters are for guidance only. The process parameters should always be optimized for the used equipment. The instructions of the equipment manufacturer should be followed. Caution should be taken when handling molten material as it is extremely hot and may cause severe burns.

Storage

Product-specific details are mentioned in the notes above. The general minimum shelf life for Premix's product is 3 years with the following conditions: 1) original package is unopened, 2) the storage area and conditions provide protection from direct sunlight and significant changes in storage temperature, 3) the product is pre-dried accordingly before use.

The information in this datasheet represents typical values obtained by us, and shall not be regarded as a product specification. The right to make any changes to the content and appearance of this document is reserved by Premix Oy. We condition that the product will be inspected and qualified by the customer for their process to meet the specific requirements set by application, processing equipment and the end product. The user of this product is held responsible for the evaluation of this product's suitability concerning applied legislation and possible patent infringements. We do not intentionally add or incorporate hazardous substances in our production.

PRE-ELEC[®] is a registered trademark of Premix.

TP14815-128