

Item Description

Item ID

PRE-ELEC[®] TPU 1512
TPU1512

Polyester-TPU extrusion compound	Typical end product	TPU/ABS Sheets
Electrically conductive	Applications	Profiles
Flexible		Sheets

PRE-ELEC[®] TPU 1512 is a conductive thermoplastic elastomer compound based on a polyester -based thermoplastic polyurethane (TPU). Conductivity is achieved by using special conductive carbon black. In addition to a low electrical resistivity, it has retained the excellent mechanical properties of the base elastomer. The grade is suitable for extrusion and injection moulding applications.

Special properties	Unit	Value	Method
Volume resistivity(*)	Ω.cm	10	PRE021
Surface resistance(*)	Ω	8E+02	IEC 61340-2-3
General properties	Unit	Value	Method
Specific gravity	g/cm3	1,27	ISO 1183
Melt flow rate at 190°C	g/10 min		ISO 1133
10.0 kg		11	
Mould shrinkage	%	1.0 - 1.3	ISO 294-4
Mechanical properties	Unit	Value	Method
Tensile strength(*)	MPa	23	ISO 527
Tensile strain at break(*)	%	810	ISO 527
Tensile stress at 100%(*)	MPa	7	ISO 527
Tensile stress at 200%(*)	MPa	9	ISO 527
Tensile stress at 300%(*)	MPa	11	ISO 527
Tensile modulus(*)	MPa	35	ISO 527
Impact strength, Charpy	kJ/m2		ISO 179
Unnotched, +23°C		NB	
Notched, +23°C		NB	
Unnotched, -20°C		NB	
Notched, -20°C		NB	
Hardness, Shore A	-	87	ISO 868

MFR is measured from granulates

Test specimen: injection moulded rod; Thickness: 10 mm, width: 4 mm

*) extruded tape; Thickness 600-800 µm

Item Description

Item ID

PRE-ELEC[®] TPU 1512
TPU1512

Visit Premix Data Center for more detailed information of our products at www.premixgroup.com/data-center-main

Processing instructions

	Unit	Processing range
Extrusion		
Cylinder temperature profile	°C	145 - 170
Die temperature profile	°C	170 - 170
Tool/Roll temperature	°C	40 - 40
Injection moulding		
Material temperature	°C	180 - 210
Mould temperature	°C	30 - 50
Injection pressure	Bar	200 - 800
Injection speed		moderate / high

Notes

Drying of the product is recommended for 2-3 hours at 80°C prior to use.

The moisture content after drying should be less than 200 ppm in order to avoid loss of properties. These parameters are for guidance only. The process parameters should always be optimized for the used equipment. The instructions of the equipment manufacturer should be followed. Caution should be taken when handling molten material as it is extremely hot and may cause severe burns.

Storage

Product-specific details are mentioned in the notes above. The general minimum shelf life for Premix's product is 3 years with the following conditions: 1) original package is unopened, 2) the storage area and conditions provide protection from direct sunlight and significant changes in storage temperature, 3) the product is pre-dried accordingly before use.

The information in this datasheet represents typical values obtained by us, and shall not be regarded as a product specification. The right to make any changes to the content and appearance of this document is reserved by Premix Oy. We condition that the product will be inspected and qualified by the customer for their process to meet the specific requirements set by application, processing equipment and the end product. The user of this product is held responsible for the evaluation of this product's suitability concerning applied legislation and possible patent infringements. We do not intentionally add or incorporate hazardous substances in our production.

PRE-ELEC[®] is a registered trademark of Premix.

TPU1512-145